

# **TEST REPORT**

No. :

Date: May. 08, 2018

Page: 1 of 3

CUSTOMER NAME:

ADDRESS:

Sample Name

: FLOOR LAMINATION FILM

Style No.

: Floor Lamination Film

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

**Test Required** 

: Slip resistance (oil-wet ramp test)

Test Method

: DIN 51130:2014-02

SGS Ref. No.

Date of Receipt

: Apr. 27, 2018

Testing Start Date

: Apr. 27, 2018

**Testing End Date** 

: May. 08, 2018

Test result(s)

: For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

Joyce Li Authorized signatory





# **TEST REPORT**

No. :

Date: May. 08, 2018

Page: 2 of 3

Test item: Slip resistance (oil-wet ramp test)

Test Method:

DIN 51130:2014-02 Testing of floor coverings - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test

Sample Description:

FLOOR LAMINATION FILM, 1000mm×500mm, 1pc, cut from original sample, see the photo(s)

#### Test Result:

Test item(s)	Test result(s)	Classification
Slip resistance (oil-wet ramp test)	Critical angle of inclination: 9.6°	R9

### Classification of oil-wet ramp test:

Classification	Angle (degrees)	
R9	6°≤X≤10°	
R10	10° <x≤19°< td=""></x≤19°<>	
R11	19° <x≤27°< td=""></x≤27°<>	
R12	27° <x≤35°< td=""></x≤35°<>	
R13	>35°	

Note: The test was performed by SGS other internal laboratory.






# **TEST REPORT**

No. :

Date: May. 08, 2018

Page: 3 of 3

### Sample photo:



End of report\*\*\*\*\*\*\*

In the territory of the People's Republic of China, the test report with CMA logo expresses that the test methods are within the scope of China Metrology Accreditation (CMA); Without CMA logo expresses that part/all of the test methods are not within the scope of China Metrology Accreditation (CMA), and just for client internal reference.

